

The PulsarLube logo is located in the top right corner of the page. It consists of the brand name "PULSARLUBE" in a bold, blue, sans-serif font. A small yellow oil drop icon is positioned below the letter "A".

PULSARLUBE



PL5

HIGH TEMPERATURE

PL5 GREASE

PL5 High Temperature grease is designed as a high temperature lubricating grease based on high quality mineral base oil and polyurea thickener. It offers good load carrying capacity and anti-wear property. This product has good adhesion, resistance to water at static and dynamic conditions and also resistant to oxidation and ageing and protecting against corrosion. PL5 High Temperature grease has a wide operating temperature range up to 160°C. In total loss lubrication systems, it can be used up to 180°C.

01.
Steel Mill



02.
Conveyor Roller



03.
Drive Roller



04.
Iron Making



01 Product Description (Benefits)

- Excellent pump ability in single point/central lubrication system
- Good resistance to ambient media, water and water steam
- Good anti-wear & load carrying capacity
- Wide service temperature (-15°C ~ 160°C)
- Mineral oil + Polyurea, Beige

02 Application Part

- Automatic grease lubricator
- Drive rollers, conveyor rollers
- Heating furnaces, drying stove
- Opening gate of bulk material equipment, cooling bed conveyor system

03 Product Data

| Test item | Unit | Test method | Result |
|-----------------------------------|----------|-------------|-----------|
| NLGI # Grade | Grade | – | 1 |
| Base Oil Viscosity, 40°C | cSt | ASTM D 445 | 420 ~ 430 |
| Worked Penetration | 0.1mm | ASTM D 217 | 310 ~ 340 |
| Dropping Point | °C | ASTM D 2265 | > 260 |
| Oil Separation | wt% | KS M 2050 | < 2.0 |
| Evaporation Loss | wt% | ASTM D 972 | < 0.50 |
| Copper Strip Corrosion | Grade | ASTM D 4048 | 1A |
| Water Washout | wt% Loss | ASTM D 1264 | < 3 |
| 4Ball Extreme Pressure Properties | kgf | ASTM D 2596 | > 200 |

Note : The above data constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field test with the product selected for a specific application

04 Suggestion of Using

Spatula, brush, lever grease guns and automatic lubricating systems

※ Storage : Recommend using within a year if the product is stored in the original closed container in a dry place

PULSARLUBE



34-12, Bangchon-Ro 955beon-Gil, Tanhyeon-Myeon, Paju-Si, Kyeongki-Do, KOREA
Tel : +82 (2) 2135-3788 | Fax : +82 (2) 2083-8485
www.pulsarlube.co.kr / sales.asia@pulsarlube.com